Mechanisms of Hydration and Setting of Ordinary Portland Cement in Simple and Complex Systems

RESEARCH SUMMARY REPORT

J



Notice

This document is disseminated under the sponsorship of the U.S. Department of Transportation in the interest of information exchange. The U.S. Government assumes no liability for the use of the information contained in this document.

The U.S. Government does not endorse products or manufacturers. Trademarks or manufacturers' names appear in this report only because they are considered essential to the objective of the document.

Quality Assurance Statement

The Federal Highway Administration (FHWA) provides high-quality information to serve Government, industry, and the public in a manner that promotes public understanding. Standards and policies are used to ensure and maximize the quality, objectivity, utility, and integrity of its information. FHWA periodically reviews quality issues and adjusts its programs and processes to ensure continuous quality improvement.

Photo credits Source: FHWA for all decorative images throughout the report.

Technical Report Documentation Page

1. Report No. FHWA-HRT-17-102		2. Government Accessic	n No.	3. Recipie	ent's Catalog No.
4. Title and Subtitle Mechanisms of Hydration and Setting of Ordinary Portland Cement in Si Complex Systems			ent in Simple and	5. Report April 201	Date 9
7. Author(s) Rolf Arvidson, Jeffrey Bullard, Josephine Cheung, Brad Chmelka, Roberts, George Scherer, Denise Silva, Patrick Zickler			Tyler Ley, Larry	6. Performing Organization Code	
 9. Performing Organization Name and Address Princeton University 4 New South Princeton, NJ 08544-0036; 				8. Performing Organization Report No.	
				10. Work Unit No.	
National Institute of Standard 100 Bureau Drive Gaithersburg, MD 20899 TMNcorp 131 Rollins Ave., Unit 4A Rockville, MD 20852	ls and Tec	hnology		11. Contr DTFH61 DTFH61	ract or Grant No. 12-H-00003, DTFH61-13-X-30003, 15-A-00003
12. Sponsoring Agency Name and Address Office of Corporate Research, Technology, and Innovation Management Federal Highway Administration 6300 Georgetown Pike			13. Type of Report and Period Covered Research Summary Report July 2012 – June 2017		
McLean, VA 22101-2296				14. Spon	soring Agency Code
15. Supplementary Notes: Contracting Officer's Represe Technical Contact: David Kue	ntative: R hn, HRT№	ichard Meininger, HRDI- 1-30	10		
16. Abstract This research summary report hydration of portland cement in real time; and develop and performance, and durability.	t provides in comple validate ii	a description of research ex and simple mixtures; d nproved computer mode	a carried out to impro evelop analytical me Is to design optimal (ove the un thods to c concrete c	derstanding of the mechanisms of lirectly observe hydration processes composition, curing methods,
The project resulted in innova of reactions. This new perspectement hydration. Computer more efficient, durable, and computer	ative analy ctive allov models ba ost-effect	vtical techniques that may wed researchers to develo ased on the new hypothe ive concrete products an	de it possible to perf op a new and clearer sis will provide engir d structures.	orm direct hypothes neers and	t micro- and nanoscale observation is to understand the mechanisms of practitioners with tools to produce
17. Key Words Concrete, portland cement, hydration, ordinary portland cement, cement hydration kinetics and modeling, advanced research, hydration mechanisms, setting of ordinary portland cement, hydration process, concrete performance, hydration breakthroughs, concrete composition.			18. Distribution Statement No restrictions. This document is available through the National Technical Information Service, Springfield, VA 22161. http://www.ntis.gov		
19. Security Classif. (of this report) Unclassified	20. Secu Unclassif	rity Classif. (of this page) ied	21. No. of Pages 20		22. Price N/A

SI* (Modern Metric) Conversion Factors

APPROXIMATE CONVERSIONS TO SI UNITS							
SYMBOL	WHEN YOU KNOW	MULTIPLY BY	TO FIND	SYMBOL			
		LENGTH					
in	inches	25.4	millimeters	mm			
ft	feet	0.305	meters	m			
yd	yards	0.914	meters	m			
mi	miles	1.61	kilometers	km			
AREA							
in ²	square inches	654.2	square millimeters	mm ²			
ft²	square feet	0.093	square meters	m ²			
yd²	square yard	0.836	square meters	m ²			
ас	acres	0.405	hectares	ha			
mi ²	square miles	2.59	square kilometers	km ²			
		VOLUME					
fl oz	fluid ounces	29.57	millimeters	mL			
gal	gallons	3.785	meters	L			
ft³	cubic feet	0.028	meters	m ³			
yd ³	cubic yards	0.765	kilometers	m ³			
	NOTE:	volumes greater than 1000 L shall be sho	wn in m³				
		MASS					
oz	ounces	28.35	grams	g			
lb	pounds	0.454	kilograms	kg			
Т	short tons (2000 lb)	0.907	megagrams (or "metric ton")	Mg (or "t")			
		TEMPERATURE (exact degrees)					
°F	Fahrenheit	5 (F-32)/9	Celsius	°C			
		or (F-32)/1.8					
		ILLUMINATION					
fc	foot-candies	10.76	lux	lx			
ft	foot-Lamberts	3.426	candela/m ²	cd/m ²			
FORCE and PRESSURE or STRESS							
lbf	poundforce	4.45	newtons	N			
lbf/in ²	poundforce per square inch	6.89	kilopascals	kPa			

APPROXIMATE CONVERSIONS FROM SI UNITS

SYMBOL	WHEN YOU KNOW	MULTIPLY BY	TO FIND	SYMBOL		
LENGTH						
mm	millimeters	0.039	inches	in		
m	meters	3.28	feet	ft		
m	meters	1.09	yards	yd		
km	kilometers	0.621	miles	mi		
		AREA				
mm ²	square millimeters	0.0016	square inches	in ²		
m ²	square meters	10.764	square feet	ft ²		
m²	square meters	1.195	square yard	yd²		
ha	hectares	2.47	acres	mi		
km ²	square kilometers	0.386	square miles	mi ²		
VOLUME						
mL	mililiters	0.034	fluid ounces	fl oz		
L	liters	0.264	gallons	gal		
m ³	cubic meters	35.314	cubic feet	ft ³		
m ³	cubic meters	1.307	cubic yards	yd ³		
		MASS				
g	grams	0.035	ounces	oz		
kg	kilograms	2.202	pounds	lb		
Mg (or "t")	megagrams (or "metric ton")	1.103	short tons (2000 lb)	Т		
TEMPERATURE (exact degrees)						
°C	Celsius	1.8C+32	Fahrenheit	°F		
		ILLUMINATION				
lx	lux	0.0929	foot-candies	fc		
cd/m ²	candela/m ²	0.2919	foot-Lamberts	ft		
FORCE and PRESSURE or STRESS						
Ν	newtons	0.225	poundforce	lbf		
kPa	kilopascals	0.145	poundforce per square inch	lbf/in ²		

*SI is the symbol for the International System of Units. Appropriate rounding should be made to comply with Section 4 of ASTM E380. (Revised March 2003)

Table of Contents

Introduction	1
Case Study: Using Advanced Analytical Techniques to Study Cement Hydration	3
Case Study: A Clearer, More Comprehensive Understanding of Hydration Mechanisms	5
Case Study: New Models to Predict Concrete Performance	7
Conclusion	9
References	11
Bibliography	12

List of Figures

Figure 1. Illustration: Experimentally acquired tomographs.	3
Figure 2. Illustration/Photo: The nano-computed x-ray tomography experimental setup.	4
Figure 3. Photo: A researcher determines the mass of a specimen on a laboratory balance.	5
Figure 4. Photo: Workers place concrete with a slip form concrete paver.	6
Figure 5. Illustration: Results of a HydratiCA run using the best available material and reaction data.	7

Figure 6. Photo: Laboratory research methods include dynamic modulus of concrete with the measurement of fundamental resonant frequency.

Introduction

oncrete is the world's most commonly used manmade construction material and second only to water as the most consumed substance on Earth.¹ Concrete can be produced in a wide variety of shapes and textures and is extremely durable, with a service life of 50 years or more in many common applications. Importantly, concrete can be made on demand and on site using portland cement, water, and aggregate materials, such as sand, gravel, crushed stone, and recycled crushed blast furnace slag. When mixed with water, portland cement forms a slurry that stays in a fluid state for several hours. During this induction phase of hydration, concrete can be transported and poured, even though the mixture is undergoing chemical and structural changes. Following the induction phase, the concrete mixture stiffens and generates heat during an acceleration phase marked by nucleation and growth of calcium hydroxide (CH) and calcium silicate hydrates (C-S-H; the dashes indicate that the compounds do not have a fixed ratio of silicon to calcium). Following this phase, heat generation drops off, but concrete continues to cure and harden. Mixtures containing high percentages of portland cement reach maximum strength within a few months. More complex mixtures with pozzolans or slag cement may continue to strengthen slowly for several years.

Although the basic concrete recipe—a combination of water, cement, and aggregate—has been in use since the early 19th century, scientists and engineers do not fully understand the chemical reactions that drive hydration and are responsible for the hardening, strength, and durability of concrete. Because of the uncertainties associated with hydration, it has not been possible to develop computer models that accurately predict the properties of the final product or explain the specific contribution of the binding agents, alternative aggregate components, or other additives. As a result, concrete is typically overdesigned by at least 10 percent to ensure that the final product meets its design performance. A better understanding of hydration would allow engineers to lower the strength overdesign "cushion" by reducing the portland cement content and thereby decreasing material costs by as much as 10 percent, without sacrificing performance, and potentially reducing volume change and cracking related to high cement content. Better computer models of hydration would also lessen concrete's environmental impact. Reduction in portland cement content will decrease the carbon dioxide (CO₂) footprint of concrete, since portland cement production releases a high amount of CO₂. Compared with other construction materials, concrete has a very low embodied CO₂ content—a measure of greenhouse gas associated with production. However, because so much concrete is used each year, it is responsible for about 8 percent of industrial CO₂ production in the United States.¹

The goal of the Federal Highway Administration's (FHWA) project, "Mechanisms of Hydration and Setting of Ordinary Portland Cement in Simple and Complex Systems," was to develop more efficient and effective ways to use concrete. Project scientists developed innovative analytical technologies to observe the mechanisms of hydration in three dimensions at the nano-, micro-, and macroscopic scales. These unprecedented observations have provided a depth of understanding of hydration mechanisms that was never before possible. Researchers used this improved understanding of hydration mechanisms to develop and validate computer models that will improve concrete composition and performance. The project was funded through FHWA's Exploratory Advanced Research (EAR) Program. Princeton University conducted the research in collaboration with research partners at the National Institute of Standards and Technology (NIST); Oklahoma State University (OSU); Rice University; University of California, Santa Barbara (UCSB); and GCP Applied Technologies, formerly W.R. Grace and Company.











In 2009, the concrete research community held an international conference-the Summit on **Cement Hydration Kinetics and** Modeling-in Quebec, Canada, to discuss research needs related to cement hydration. U.S. sponsors of the summit included FHWA. **NIST**, and the National Science Foundation. Following the summit, NIST and FHWA issued a joint publication outlining their vision for needed research, NIST **Special Publication 1138: Paving** the Way for a More Sustainable **Concrete Infrastructure: A Vision** for Developing a Comprehensive **Description of Cement Hydration** *Kinetics.*² The EAR Program project, "Mechanisms of Hydration and Setting of Ordinary **Portland Cement in Simple and** Complex Systems," advances the joint research vision identified at the summit and expressed in the joint publication: "... focused experimental and computational modeling research that will provide the knowledge and translate it to industry tools for improved cements, mixture design, and service life prediction of concrete in service."



Figure 1. Illustration: Experimentally acquired tomographs. ((a) Initial particle configuration on a tungsten needle. (b) After 7 hours of reaction in an aqueous solution with initial CH concentration of 15 mmol L^{-1} . C_3S particles are dark gray, the tungsten needle is light gray, and the hydration products are shown as transparent.) ©*The American Ceramic Society*.³

Case Study: Using Advanced Analytical Techniques to Study Cement Hydration

Researchers at OSU focused on the use of advanced tomography and fluorescence imaging to experimentally visualize cement hydration at the micro- and nanoscales. The OSU team used a combination of nano-computed tomography (nCT) to capture the three-dimensional (3D) structure and nano x-ray fluorescence to reveal the 3D chemistry of cement before, during, and after hydration. This technique allowed the researchers to see changes in density and chemistry caused by hydration. Similar to x-ray computed tomography commonly used in medical sciences for nondestructive imaging of internal biological structures, nCT combines a series of images acquired at small angles of rotation around the target to produce a 3D model or tomograph. The relatively low-energy-level x-rays used

in nCT make it possible to construct 3D tomographs of cementitious and geologic materials. Interpretation of the images, and alignment of the images with the compositional data, required researchers to create the sophisticated software needed for analysis of huge quantities of data.

Using nCT, the OSU researchers directly observed the changing microstructure of tricalcium silicate (C_3S), a portland cement component that is primarily responsible for rapid hardening and plays an important role in the initial set and early strength of concrete. The research team used 3D microstructure imaging to make point-by-point comparisons of observed particle reactions and computer simulations of particle reactions in an aqueous

Case Study: Using Advanced Analytical Techniques to Study Cement Hydration (Cont.)

solution of CH at a resolution of 50 nm and sometimes as low as 15 nm depending on the experiment. The outputs of these analytical techniques developed at OSU have been used as a direct input in hydration models.

At UCSB, researchers focused on the development, demonstration, and use of new methods of nuclear magnetic resonance (NMR) spectroscopy to characterize at a molecular level the compositions, structures, and properties of cementitious materials. This characterization relied on combinations of powerful solid-state NMR capabilities, such as dynamic-nuclearpolarization (DNP) enhancement techniques, to identify and quantify surface species in hydrating cementitious materials with unprecedented sensitivity and resolution. The work has led to new, significant, and molecularlevel insights into the detailed compositions, structures, and site-specific interactions of cementitious materials during hydration. Solid-state silicon-29 (29Si), hydrogen-1 (¹H), calcium-43 (⁴³Ca), and magnesium-25 (²⁵Mg) NMR measurements were conducted on triclinic C₂S,

monoclinic C_3S , tricalcium aluminate (C_3A), and white portland cements to identify and quantify the molecular species present, their transient formation or depletion under hydrating conditions, and estimated mean thicknesses of early hydration layers.

The DNP-NMR analyses examined the adsorption of retarder species like saccharides or phosphonates. The results enabled the molecular origins of retarder properties and the performances to be determined. This determination included the specific atomic-level interactions that account for competitive adsorption of dilute retarder quantities versus water at silicate surfaces, which dramatically slow the hydration of low-surfacearea silicate particles. The UCSB researchers made key advances, including the use of 2D and DNP-enhanced NMR measurements, to yield a new understanding of the compositions and structures of hydrating cementitious materials for industrially relevant materials and formulations.



Figure 2. Illustration/Photo: The nano-computed x-ray tomography experimental setup. ((a) This is a diagram of the setup. (b) This setup has a cement C_3 S particle on a tungsten needle in a solution that allows the particle to hydrate during the experiment.) ©*The American Ceramic Society*.³



Figure 3. Photo: A researcher determines the mass of a specimen on a laboratory balance. Source: FHWA.

Case Study: A Clearer, More Comprehensive Understanding of Hydration Mechanisms

he important analytical and imaging advances described above revealed features of the hydration process that had never before been directly observed. The rapid reaction with water creates pits in the surface of C_3S particles that quickly fill with hydration products having a high Ca/silicate ratio. One remarkable observation was that voids form in the paste after about 1 hour of hydration. At the start of the acceleration period, when the solute concentration drops because of rapid precipitation of C-S-H, the quantity of voids decreases and their size distribution changes. These voids influence the strength of the hardened paste.

The researchers have developed a new hypothesis to explain the induction and acceleration periods. This hypothesis is supported by numerous observations made at the nano- and microscale levels for this project:

1. Nanoscale measurements show that there are certain regions within C_3S particles, probably associated with crystalline defects, that dissolve more rapidly than others.

Case Study: A Clearer, More Comprehensive Understanding of Hydration Mechanisms (Cont.)

- These regions form etch pits that are quickly filled with C-S-H, perhaps because of the high ion concentration in the pit.
- As these fast-reacting regions continue to dissolve, the ions must diffuse through the newly formed C-S-H, so the ion concentration within the pores of the C-S-H will increase at a much higher rate than in the rest of the liquid in the cement mixture.
- 4. Soon, other solid products, such as portlandite, CH, begin forming within the pits.

- 5. The solids forming within the pores of the C-S-H reduce ion transport, slowing the reaction and causing the induction period. Ion concentrations continue to build in the bulk solution until they start forming solid hydration products such as CH.
- Once these solid products begin to form, the concentration of ions in the solution drops and the nano-CH and sulfate from gypsum or hemihydrate (CaSO_{4.2}H₂O or CaSO_{4/1.2} H₂O) dissolve.
- 7. This opens the pores of the C-S-H and allows rapid reaction of the fast-reacting regions, resulting in the start of the acceleration period.

Figure 4. Photo: Workers place concrete with a slip form concrete paver. Source: FHWA.





Figure 5. Illustration: Results of a HydratiCA run using the best available material and reaction data. ((a) The initial sample before hydration, a coarse-grained replication, voxel-by-voxel, of the system observed by the OSU group. (b) Changes in the C₃S particles after 7 hours of simulated hydration, with the hydration product indicated as a transparent shell form in comparison to figure 1. (c) The simulated distribution of Ca(OH)₂ [green] and C-S-H [transparent].) ©*The American Ceramic Society*.³

Case Study: New Models to Predict Concrete Performance

Researchers with the NIST model development group used observational findings to advance the state of cement hydration models and develop a validated, user-friendly engineering tool that could reliably predict the performance of concrete in the field and provide insights into how to manipulate that performance. The primary focus of the NIST research activities was to improve the simulation performance of HydratiCA, a kinetic cellular automaton model based on fundamental chemical reaction kinetic principles. HydratiCA is verified for some simple cementitious reactions but has historically lacked experimental measurement data needed for simulations of more complex hydration behavior. Potentially the most powerful model for predicting reaction rates and

microstructure development, HydratiCA is also the most complex and computationally intensive. The NIST researchers have managed important breakthroughs that make HydratiCA more robust and far more efficient. In addition to integrating the experimental findings generated by the UCSB and OSU research teams, the NIST team has parallelized the HydratiCA model to run on multiple central processing units at once and optimize communications among processors, resulting in an efficiency boost of 40 to 200 times. This allows HydratiCA to model cement hydration in real time: simulating 24 hours of hydration now takes 24 hours of run time, rather than several weeks or months.

Case Study: New Models to Predict Concrete Performance (Cont.)

In addition to enhancements to HydratiCA, the NIST team incorporated experimental results into the VCCTL (virtual cement and concrete testing laboratory) website and THAMES (thermodynamic hydration and microstructure evolution simulator). VCCTL has a user-friendly interface, which is connected to a materials database that allows a user to model a 3D microstructure of a cement mix and the hydration of that mix. THAMES builds on the capabilities of VCCTL by allowing small amounts of other materials to be added to the microstructure and determining the impact of these changes on hydration. Unlike VCCTL, THAMES is built with underlying thermodynamics data, which allows for greater accuracy in modeling hydration. Researchers at Princeton University developed a computer program called SimBNG that models boundary nucleation and growth (BNG) of C-S-H, the cement hydration product that is primarily responsible for strength in cured concrete. A key goal for SimBNG development in this project was to apply as many external constraints on the model as possible, while maintaining quick run times and accurate results. The group at Princeton developed a method for supercritical drying of cement paste that preserves the delicate microstructure of the material without the artifacts that usually result from the capillary pressure exerted during conventional drying.

Figure 6. Photo: Laboratory research methods include dynamic modulus of concrete with the measurement of fundamental resonant frequency. *Source: FHWA*.



Conclusion

he EAR Program's "Mechanisms of Hydration and Setting of Ordinary Portland Cement in Simple and Complex Systems" project has generated an extraordinary new understanding of the critical processes involved in cement hydration. The range of accomplishments includes sensitive and innovative analytical methods and a deepened understanding of fundamental chemical processes governing hydration; with this understanding, practitioners can plan concrete projects that use resources more efficiently and produce structures that are stronger and more durable.





References

- ¹ Choate, W.T. (2003). Energy and Emission Reduction Opportunities for the Cement Industry, Department of Energy, Office of Energy Efficiency and Renewable Energy, Columbia, MD. Available online: <u>https://www1.eere.energy.gov/</u> <u>manufacturing/industries_technologies/imf/pdfs/eeroci_</u> dec03a.pdf, last accessed April 28, 2019.
- ² Bullard J.W., Biernacki J.J., Constantiner C., Meininger R., Juenger M., Cheung J.H., Hansen W., Hooten R.D., Luttge A., and Thomas J.J. (2013). "Paving the Way for a More Sustainable Concrete Infrastructure: A Vision for Developing

a Comprehensive Description of Cement Hydration Kinetics." Special Publication Report - 1138, National Institute of Standards and Technology Publications. Available online: https://www.nist.gov/publications/paving-way-moresustainable-concrete-infrastructure-vision-developingcomprehensive, last accessed May 10, 2019.

³ Bullard J.W., Hagedorn J., Ley M.T., Hu Q., Griffin W., and Terrill J.E. (2018). "A critical comparison of 3D experiments and simulations of tricalcium silicate hydration." *Journal of the American Ceramic Society*, 101, pp. 1453-1470.



Bibliography

Bellmann, R., and Scherer, G.W. (2018). "Analysis of C-S-H Growth Rates in Supersaturated Conditions." *Cement and Concrete Research*, 103 (January), pp.236–244. Available online: http://dx.doi.org/10.1016/j.cemconres.2017.05.007, last accessed April 28, 2019.

Briese, L., Arvidson, R.S., and Luttge, A. (2017). "The Effect of Crystal Size Variation on the Rate of Dissolution—A Kinetic Monte Carlo Study." *Geochimica et Cosmochimica Acta*, 212 (September), pp.167–175. Available online: <u>https://doi. org/10.1016/j.gca.2017.06.010</u>, last accessed April 28, 2019.

Bullard J.W., Griffin W., Hagedorn J., Hu Q., Ley M.T., and Terrill J.E. (2018). "A critical comparison of 3D experiments and simulations of tricalcium silicate hydration." *Journal of the American Ceramic Society*, 101, pp. 1453–1470. Available online: https://doi.org/10.1111/jace.15323, last accessed April 28, 2019.

Bullard, J.W., and Scherer, G.W. (2016). "Solid Solution Model for C-S-H." *Journal of the American Ceramic Society*, 99 (12), pp.4137–4145.

Bullard, J.W., Scherer, G.W., and Thomas, J.J. (2015). "Time Dependent Driving Forces and the Kinetics of Tricalcium Silicate Hydration." *Cement and Concrete Research*, 74, pp.26–34.

Feng, P., Brand, A.S., Chen, L., and Bullard, J.W. (2017). "In Situ Nanoscale Observations of Gypsum Dissolution by Digital Holographic Microscopy." *Chemical Geology*, 460 (June), pp.25– 36. Available online: <u>https://www.sciencedirect.com/science/</u> article/pii/S000925411730195X, last accessed April 28, 2019.

Feng, P., Garboczi, E.J., Miao, C., and Bullard, J.W. (2015). "Microstructural Origins of Cement Paste Degradation by External Sulfate Attack." *Construction and Building Materials*, *96*, pp.391–403.

Fonseca, P.C., and Scherer, G.W. (2015). "An Image Analysis Procedure to Quantify the Air Void System of Mortar and Concrete." *Materials and Structures*, *48* (10), pp.3087–3098.

Hu, Q., Aboustait, M., Kim, T., Ley, M.T., Bullard, J.W., Scherer, G.W., Hanan, J.C., Rose, V., Winarski, R., and Gelb, J. (2016). "Direct Measurements of 3D Structure, Chemistry and Mass Density During the Induction Period of C₃S Hydration." *Cement* and Concrete Research, 89 (November), pp.14–26. Available online: <u>http://dx.doi.org/10.1016/j.cemconres.2016.07.008</u>, last accessed April 28, 2019.

Hu, Q., Aboustait, M., Kim, T., Ley, M.T., Hanan, J.C., Bullard, J.W., Winarski, R., and Rose, V. (2016). "Direct Three-Dimensional Observation of the Microstructure and Chemistry of C₃S Hydration." *Cement and Concrete Research, 88* (October), pp.157–169. Available online: <u>http://dx.doi.org/10.1016/j.</u> cemconres.2016.07.006, last accessed April 28, 2019.

Hu, Q., Aboustait, M., Ley, M.T., Hanan, J.C., Rose, V., and Winarski, R. (2014). "Combined Three-Dimensional Structure and Chemistry Imaging with Nanoscale Resolution." *Acta Materialia*, 77, pp.173–182.

Li, X., Grasley, Z.C., Bullard, J.W., and Garboczi, E.J. (2015). "Computing the Time Evolution of the Apparent Viscoelastic/ Viscoplastic Poisson's Ratio of Hydrating Cement Paste." *Cement and Concrete Composites*, *56*, pp.121–133.

Pustovgar, E., Sangodkar, R.P., Andreev, A.S., Palacois, M., Chmelka, B.F., Flatt, R.J., and d'Espinose de Lacaillerie, J.-B. (2015). "Understanding Silicate Hydration from Quantitative Analyses of Hydrating Tricalcium Silicate." *Nature Communications*, 7, pp.10952.

Sangodkar, R.P., Smith, B.J., Gajan, D., Rossini, A.J., Roberts, L.R., Funkhouser, G.P., Lesage, A., Emsley, L., and Chmelka, B.F. (2015). "Influences of Dilute Organic Adsorbates on the Hydration of Low-Surface-Area Silicates." *Journal of the American Chemical Society*, 137, pp.8096–8112.

Scherer, G.W., and Bellmann, F. (2018). "Kinetic Analysis of C-S-H Growth on Calcite." *Cement and Concrete Research*, 103 (January), pp.226–235. Available online: <u>http://dx.doi.</u> org/10.1016/j.cemconres.2016.07.017, last accessed April 28, 2019.

Stoian, J., Oey, T., Bullard, J.W., Huang, J., Kumar, A., Balonis, M., Terrill, J., Neithalath, N., and Sant, G. (2015). "New Insights into the Prehydration of Cement and Its Mitigation." *Cement and Concrete Research*, 70, pp.94–103.

Zhang, Z., and Scherer, G.W. (2017). "Supercritical Drying of Cementitious Materials." *Cement and Concrete Research*, 99, pp.137–154.



Getting Involved with the EAR Program

To take advantage of a broad variety of scientific and engineering discoveries, the EAR Program involves both traditional stakeholders (State department of transportation researchers, University Transportation Center researchers, and Transportation Research Board committee and panel members) and nontraditional stakeholders (investigators from private industry, related disciplines in academia, and research programs in other countries) throughout the research process.

Learn More

For more information, see the EAR Program website at https://highways.dot.gov/research/exploratoryadvanced-research. The site features information on research solicitations, updates on ongoing research, links to published materials, summaries of past EAR Program events, and details on upcoming events.







Federal H'ghway Adm'n'strat'on

EXPLORATORY ADVANCED **RESEARCH**

EXPLORATORY ADVANCED RESEARCH

FHWA-HRT 17 102 HRTM-30/06-19 (WEB)E