

CHANGE 6

DATE March 10, 1980

ADVISORY CIRCULAR

CHANGE



DEPARTMENT OF TRANSPORTATION
Federal Aviation Administration
Washington, D.C.

Subject: Change 6 to STANDARDS FOR SPECIFYING CONSTRUCTION OF AIRPORTS--
Issues a New Standard

1. PURPOSE. This Change adds Item P-402, Porous Friction Course, a new standard developed through research and construction experience.

The Change number and date of changed material is carried at the top of each page.

PAGE CONTROL CHART

Remove Pages	Dated	Insert Pages	Dated
291-302	10/24/74	291 and 292 293-302 302-1 thru 302-11	3/10/80 3/10/80 3/10/80

William V. Vitale
WILLIAM V. VITALE
Director, Office of Airport Standards

Suggest filing this transmittal at the back of the AC. It will provide a reference authority for changes, a method of determining that all Changes have been received, and a check for determining if the AC contains the proper pages.

Initiated by: AAS-200

ITEM P-401 BITUMINOUS SURFACE COURSE

MATERIAL REQUIREMENTS

ASTM D 242	Mineral Filler for Bituminous Paving Mixtures
ASTM D 490	Tar
ASTM D 946	Asphalt Cement for Use in Pavement Construction
ASTM D 3381	Viscosity-Graded Asphalt Cement for Use in Pavement Construction
AASHTO M 226	Viscosity Graded Asphalt Cement

SPECIFICATION REQUIREMENTS

The Asphalt Institutes's Specification Series No. 1 (SS-1)	Model Construction Specifications for Asphalt Concrete and Other Plant-Mix Types
---	---

ITEM P-402 POROUS FRICTION COURSE
(Central Plant Hot Mix)

1.5

1.6

1. DESCRIPTION

3

1.1 This item shall consist of an open-graded, bituminous surface course composed of mineral aggregate and bituminous material, mixed in a central mixing plant, and placed on a prepared surface in accordance with these specifications and shall conform to the dimensions shown on the plans.

6

6

8

8

9

***** 13.1

The porous friction course (PFC) is designed as a free-draining, wearing surface of uniform thickness which will provide a skid resistant and hydroplane resistant surface for aircraft landing and takeoff operations.

14

15

16

16

***** 17.2

2. MATERIALS

22

2.1 AGGREGATE. The aggregate shall consist of crushed stone, crushed gravel, or crushed slag with or without other inert finely divided mineral aggregate. The aggregate shall be composed of clean, sound, tough, durable particles, free from clay balls, organic matter, and other deleterious substances. The crushed aggregate portion which is retained on the 3/8-inch (9.5 mm) sieve shall not contain more than 15 percent by weight of flat or elongated particles as defined in ASTM D693.

25

27

28

32

34

35

36

36

The crushed aggregate portion which is retained on the No. 4 (4.75 mm) sieve shall not show a percentage of wear greater than [** ____] when tested in accordance with ASTM C131.

38

38

40

***** 44.1

Percentage of wear shall not exceed 30. However, if local aggregates cannot meet this requirement and hauling of aggregates that meet the requirement is economically infeasible, the Engineer may waive the requirement for a higher percentage loss than specified if local aggregates have proven satisfactory performance under similar conditions of service.

47

47

48

48

49

50

50

***** 51.2

The crushed aggregate portion which passes the 3/4-inch (19.0 mm) sieve and is retained on the No. 4 (4.75 mm) sieve shall not show a total weighted average loss greater than [** ____] percent in sodium sulfate solution or a magnesium soundness loss exceeding [** ____] percent after 5 cycles when tested in accordance with ASTM C88. The soundness test (ASTM C88) may be waived by the Engineer where porous friction course will not be subjected to freezing and thawing.

56

58

60

60

62

63

64

64

ITEM P-402 POROUS FRICTION COURSE
(Central Plant Hot Mix)1.5
1.6

 Sodium sulfate loss should not exceed 9 percent; magnesium loss should not exceed 12 percent. In certain specific cases where aggregates cannot economically comply with these maximums, aggregates with a higher percentage loss may be specified, provided satisfactory service has been demonstrated.

68.1
70
71
72
73
74
74
74
75.2

The crushed aggregate portion passing the 3/4-inch (19.0 mm) sieve and retained on the 1/4-inch (6.3 mm) sieve shall have an estimated coated area "above 95 percent" when tested in accordance with ASTM D1664. If coated area is "below 95 percent," the asphalt shall be treated with an antistripping agent. The amount of antistripping agent used shall be sufficient to produce a coated area "above 95 percent."

80
81
82
83
83
84
84
84

If crushed gravel aggregate is used, that portion retained on the No. 8 (2.36 mm) sieve and each succeeding coarser sieve shall contain at least 75 percent by weight of crushed pieces having two or more fractured faces and at least 90 percent by weight of particles containing one or more fractured faces. To count as a fractured face, the area of the fractured surface must be at least 75 percent of the smallest midsectional area of the particle being examined. To count as two fractured faces, the angle between two contiguous planes of fracture should be 30 degrees or more.

87
87
90
92
93
94
94
97
97
97

If crushed slag aggregates are used, the slag shall be air-cooled from the blast furnace process and shall have a compacted unit weight of not less than 70 pounds per cubic foot (1.12 Mg/cu.m) when tested in accordance with ASTM C29.

100
101
102
102

2.2 FILLER. If filler, in addition to that naturally present in the aggregate, is necessary, it shall meet the requirements of ASTM D242. When mineral filler is required to be batched separately, hydrated lime in the amount of 1.5 percent maximum by weight of the total aggregate shall be batched as part of the added mineral filler. No additional compensation will be allowed the Contractor for furnishing and using hydrated lime or other approved mineral filler that may be required by this specification.

106
108
109
110
111
112
112
113
113

2.3 BITUMINOUS MATERIAL. The bituminous material shall conform to the following requirements: [** ____.]

116
117

ITEM P-402 POROUS FRICTION COURSE
(Central Plant Hot Mix)1.5
1.6

 The Engineer shall specify the type and grade of bituminous material based on geographical location and climatic conditions. The maximum mixing temperature and controlling specification shall also be specified. Types of material are listed below.

121.1
122
123
124
126
126

Type and Grade		Specification	Maximum Mixing Temperature		
			deg. F	deg. C	
Penetration Grade	60-70	ASTM D946	335	170	128
	85-100		325	165	129
	120-150		310	155	130
	200-300		295	146	131
					132
Viscosity Grade	AC-5	AASHTO M226	295	145	133
	AC-10		315	155	134
	AC-20		330	165	135
					136
Viscosity Grade	AR-2000	ATSM D3381	325	165	137
	AR-4000		325	165	138
	AR-8000		325	165	139
					140
					141
					142
					143
					144
					145
					146

In extremely hot climates, the Engineer should consider using AC-40 in lieu of AC-20. Experience of constructing PFC overlays in hot climates has shown the need for using a stiffer asphalt cement.

150
151
151
151

The Engineer may also want to consider using a neoprene additive in the asphalt cement. This modification exhibits improved elasticity, less tendency to flow, and greater stability at extreme temperatures. No more than 1-1/2 percent of the neoprene additive should be used in the total asphalt cement required, and it should be rejected if heated above 340 degrees F (171 degrees C).

153
154
156
157
157
158
158
158

159.2

3. COMPOSITION

164

3.1 COMPOSITION OF MIXTURES. The porous friction course shall be composed of a mixture of aggregate, filler, bituminous material, and antistripping agent (if required). The several aggregate fractions shall be sized, graded, and combined in the proportions that meet the requirements of the job mix formula.

167
169
171
173
173

ITEM P-402 POROUS FRICTION COURSE
(Central Plant Hot Mix)1.5
1.6

3.2 JOB MIX FORMULA. No bituminous mixture shall be produced for payment until the Contractor has submitted samples of the materials and the Engineer has established a satisfactory job mix formula for each mixture to be used. The job mix formula for each mixture shall be in effect until modified in writing by the Engineer. The job mix formula for each mixture shall establish a single percentage passing each required sieve size, a single percentage of bituminous material to be added to the aggregate, and a single temperature for the mixture as it is discharged into the hauling units.

176
176
177
179
179
180
181
181
181
182
182
182
182
186.1

The job mix formula should be determined by taking samples from the plant's hot bins by trial runs. Due to the variability in normal plant operations, the job mix formula based on stockpile sampling could give misrepresentative results.

187
188
189
189
189
189
190.2

The combined aggregate shall be of such size that the percentage composition by weight, as determined by laboratory sieves, will conform to the gradation shown in Table 1 when tested in accordance with ASTM C136. The range of bituminous contents shown in Table 1 is representative of most crushed stone and crushed gravel aggregates and is not intended to limit the bituminous content established in the job mix formula.

195
197
197
199
200
201
201

The gradations in Table 1 represent the limits which shall determine the suitability of the aggregate for use from the sources of supply. The aggregate, as finally selected, shall have a gradation within the limits designated in Table 1 and shall not vary from the low limit on one sieve to the high limit on the adjacent sieve, or vice versa, but shall be uniformly graded from coarse to fine.

203
204
207
207
207
208
210
210

ITEM P-402 POROUS FRICTION COURSE
(Central Plant Hot Mix)1.5
1.6TABLE 1. AGGREGATE - POROUS FRICTION COURSE213
214

Sieve Size	Percentage by Weight Passing Sieve	
3/4 in. (19.0 mm)	*	219
1/2 in. (12.5 mm)	*	220
3/8 in. (9.5 mm)	*	221
No. 4 (4.75 mm)	*	222
No. 8 (2.36 mm)	*	223
No. 30 (600 micro m)	*	224
No. 200 (75 micro m)	*	225
Compacted Thickness	*	227
Bituminous Content	5-7 percent by weight of total mix	229 230

 The aggregate gradation band applicable to a project shall be specified by the Engineer from the gradations in this note. The gradation shall be inserted in Table 1. Insert points are denoted by asterisks.

AGGREGATE - POROUS FRICTION COURSE

235.1

Sieve Size	:	Percentage by Weight Passing Sieves	:	
3/4 in. (19.0 mm)	:	100	:	249
1/2 in. (12.5 mm)	70-100		100	250
3/8 in. (9.5 mm)	45-75		80-100	251
No. 4 (4.75 mm)	20-40		20-40	252
No. 8 (2.36 mm)	12-20		12-20	253
No. 30 (600 micro m)	8-14		8-14	254
No. 200 (75 micro m)	3-5		3-5	255
Compacted Thickness	1 in. (25 mm)	3/4 in. (19 mm)		257
Bituminous Content	5-7 percent by weight of total mix			259 260

ITEM P-402 POROUS FRICTION COURSE
(Central Plant Hot Mix)1.5
1.6

The gradations shown are based on aggregates of uniform specific gravity, and the percentages passing the various sieves will be subject to appropriate adjustments by the Engineer when aggregates of varying specific gravities are used. The adjustments to the job mix gradation curve should result in a curve of the same general shape as the median curve of the gradation band in Table 1 and fall within the gradation band.

264
265
266
266
267
268
269
269

Appendix A of The Asphalt Institute's Manual Series No. 2 (MS-2), 4th Edition, March 1975, contains a convenient procedure for "adjusting" the job mix gradation when aggregates of nonuniform specific gravity are proposed for use.

271
274
275
275
275

The bituminous content of porous friction courses shall be expressed as a percentage of the total mix by weight and shall be estimated by the Engineer on the basis of laboratory tests of the aggregates the Contractor proposes to use and the bituminous material specified.

277
278
278
279
280

The bituminous content estimated by the Engineer shall be within plus or minus 1 percent of the value obtained from the formula:

282
283
283

$$2 K \text{ (sub c) } + 4.0$$

285

where K (sub c) is the surface constant for that part of the total dry aggregate that will pass a 3/4-inch (19.0 mm) sieve and be retained on the No. 4 (4.75 mm) sieve. Procedures for determining K (sub c) are contained in Chapter IV of The Asphalt Institute's Manual Series No. 2 (MS-2). The bituminous content so estimated is the percentage by weight of the total dry aggregates and must be converted to the percent by weight of the total mix in the approved job mix formula.

288
289
290
291
292
293
293
294
294
295.2

The job mix tolerances shown in Table 2 shall be applied to the job mix formula to establish a job control grading band. The full tolerances will still apply if application of the job mix tolerances results in a job control grading band outside the master grading band.

300
302
302
303
303

ITEM P-402 POROUS FRICTION COURSE
(Central Plant Hot Mix)1.5
1.6TABLE 2. JOB MIX FORMULA TOLERANCES
(Based on a Single Test)305
306
307

Material	Tolerance - Plus or Minus	
		309
		310
Aggregate passing No. 4 sieve or larger	7.0 percent	312
Aggregate passing No. 8 and No. 30 sieves	4.0 percent	313
Aggregate passing No. 20 sieve	2.0 percent	314
Bitumen	0.40 percent	315
Temperature of mix	26 deg. F (14 deg. C)	316
		317
		318
		319

If a change is made in any component of the bituminous mix, a new job mix formula shall be established and approved by the Engineer before any additional material on the project is produced and placed. When unsatisfactory results or other conditions make it necessary, the Engineer may establish a new job mix formula.

322
323
324
325
326

3.3 TEST SECTIONS. Prior to full plant production, the Contractor shall prepare a quantity of PFC mixture according to the job mix formula. The amount of mixture should be sufficient to construct a test section [**] long and [**] wide. The test area will be designated by the Engineer. The mixture shall be placed in two sections and shall be of the same depth specified on the plans. The underlying pavement on which the test section is to be constructed shall be the same as the remainder of the course represented by the test section. The equipment to be used in construction of the test section shall be the same type and weight to be used on the remainder of the course represented by the test section.

329
330
331
335
337
338
338
340
340
341
341

If the test section should prove to be unsatisfactory, the necessary adjustments to the mix design, plant operation, and/or rolling procedures shall be made. Additional test sections, as required, shall be constructed and evaluated for conformance to the specifications. When test sections do not conform to specification requirements, the pavement shall be removed and replaced at the Contractor's expense. Full production shall not begin without approval of the Engineer. Test sections will be paid for in accordance with Paragraph 402-6.1.

344
346
348
348
349
350
351
352
352

ITEM P-402 POROUS FRICTION COURSE
(Central Plant Hot Mix)1.5
1.6

The test section should be a minimum of 50 feet (15 m) long and 20 feet (6 m) wide. The test section affords the Contractor and the Engineer an opportunity to determine the quality of the mixture in place, as well as performance of the plant and laydown equipment. Wherever possible, the test section should be placed in an area where it will receive little or no traffic so that marginal quality trial runs can be safely left in place.

356.1
358
359
359
360
363
363
364
364
364
365.2

4. CONSTRUCTION METHODS

370

4.1 WEATHER AND SEASONAL LIMITATIONS. The porous friction course shall be constructed only on a dry surface when the atmospheric temperature is 50 degrees F (10 degrees C) and rising (at calm wind conditions) and when the weather is not foggy or rainy.

373
373
374
375
375

4.2 BITUMINOUS MIXING PLANT. The bituminous mixing plant shall include all facilities or equipment necessary to produce the bituminous mix. The facility shall include auxiliary items such as stockpile storage areas, equipment to construct and maintain the stockpiles, cold bin or silo storage, and the feeder system from the cold bin or silo storage to the drier(s).

378
378
379
380
381
381

Plants used for the preparation of bituminous mixtures shall conform to all requirements under (a), except that scale requirements shall apply only where weight proportioning is used. In addition, batch mixing plants shall conform to the requirements under (b), and continuous mixing plants shall conform to the requirements under (c).

383
385
385
386
388
388

(a) Requirements for All Plants. Mixing plants shall be of sufficient capacity to adequately produce the quantity of bituminous mixture for the proposed construction.

391
391
392

(1) Aggregate stockpiles. Sufficient storage space shall be provided so that each aggregate size can be kept in separate stockpiles. The stockpile will be constructed in uniform layers by using a clamshell or other approved method to prevent segregation. The use of bulldozers in stockpiling aggregates will not be permitted. The storage yard shall be neat and orderly, and the separate stockpiles shall be readily accessible for sampling.

395
395
396
396
397
398
399
399

(2) Cold bins. The plant shall have an adequate number of cold bins or silos for each aggregate size. These cold bins or silos shall be constructed so that no overflow from one bin to the other occurs. They shall also have individual,

402
403
403
404

ITEM P-402 POROUS FRICTION COURSE
(Central Plant Hot Mix)1.5
1.6

adjustable outlet devices to provide a uniform and continuous flow of materials in the desired proportions. Prior to producing any mixture, the Contractor shall furnish the Engineer with calibrations showing the rate of feed of each aggregate for the cold bin or silo in which it is to be used. Change of material or change of cold bin or silo will require new calibrations. The calibration shall show the rate of feed per minute per unit of opening or setting of feed.

405
407
407
408
409
410
410
410

(3) Feeder for drier. The plant shall be provided with accurate mechanical means for uniformly feeding the aggregate into the drier to obtain uniform production and temperature.

413
414
415
415

(4) Drier. The plant shall include a drier(s) which continuously agitates the aggregate during the heating and drying process.

418
419
419

(5) Screens. Plant screens, capable of screening all aggregates to the specified size and proportions and having normal capacities in excess of the full capacity of the mixer, shall be provided.

423
423
424
425

(6) Dust collector. The plant shall be equipped with a dust collector to waste any material or to return all or any part of the material uniformly to the mixture as directed.

428
429
430

(7) Hot bins. The plant shall include hot bins of sufficient capacity to supply a mixer operating at full capacity. Hot bins shall be arranged to assure separate and adequate storage of appropriate fractions of the aggregates. When used, separate dry storage shall be provided for batching mineral filler and hydrated lime. The plant shall be equipped to proportion and feed the material into the mixer. Each bin shall be provided with overflow pipes located to prevent backup of material in other compartments or bins. Each compartment shall be provided with its individual outlet gate to prevent leakage. The gates shall cut off quickly and completely. Hot bins shall be constructed so that samples may be obtained readily. Hot bins shall be equipped with adequate telltale devices which indicate the position of the aggregates in the bins at the lower quarter points.

433
434
435
436
437
438
439
440
441
441
443
444
444
445
445

(8) Plant scales. Scales shall be accurate to 0.5 percent of the required load. Poises shall be designed to be locked in any position to prevent unauthorized change of position. In lieu of plant scales, the Contractor may provide an approved automatic printer system to print the weights of the material delivered, provided the system is used in conjunction with an approved automatic batching and mixing control system. Such weights shall be evidenced by a weigh ticket for each load.

448
449
449
449
451
451
452
452
452
453

ITEM P-402 POROUS FRICTION COURSE
(Central Plant Hot Mix)1.5
1.6

Scales shall be inspected for accuracy and sealed as often as the Engineer may deem necessary. The Contractor shall have on hand not less than ten 50-pound (23 kg) weights for testing the scales.

454
455
456
456

(9) Equipment for preparation of bituminous material. Tanks for the storage of bituminous material shall be equipped to heat and hold the material at the required temperatures. Heating shall be accomplished by approved means so that flames will not contact the tank. The circulating system for the bituminous material shall be designed to assure proper and continuous circulation during the operating period. Provision shall be made for measuring quantities and for sampling the material in the storage tanks.

458
459
461
461
462
463
464
464
465

(10) Bituminous control unit. Satisfactory means, either by weighing or by metering, shall be provided to obtain the specified amount of bituminous material in the mix. Means shall be provided for checking the quantity or rate of flow of bituminous material into the mixer.

468
470
471
471
471
471

(11) Thermometric equipment. An approved thermometer of adequate range shall be placed in the bituminous feed line at a suitable location near the discharge valve of the mixer unit. The plant shall also be equipped with an approved thermometric instrument placed at the discharge chute of the dryer to indicate the temperature of the heated aggregates.

474
474
475
476
477
477

(12) Safety requirements. Adequate and safe stairways to the mixer platform and sampling points shall be provided. Guarded ladders to other plant units shall be placed at all points where accessibility to plant operations is required. Accessibility to the top of truck bodies shall be provided by a suitable device to enable the Engineer to obtain mixture samples and temperature data. A means shall be provided to raise and lower scale calibration equipment, sampling equipment, and other similar equipment between the ground and the mixer platform. All belts, gears, pulleys, chains, sprockets, projecting setscrews, keys, and other dangerous moving parts shall be guarded to prevent inadvertent contact by workmen or other moving equipment. Ample and unobstructed passage shall be maintained at all times in and around the truck loading area. This area shall be kept free of drippings from the mixing platform.

480
480
481
482
483
484
485
487
488
493
494
495
496
497
497

(13) Truck scales. The bituminous mixture shall be weighed on approved scales furnished by the Contractor or on public scales at the Contractor's expense. Scales shall be inspected for accuracy and sealed as often as the Engineer deems necessary.

500
501
502
502
502(b) Requirements for Batching Plants

504

ITEM P-402 POROUS FRICTION COURSE
(Central Plant Hot Mix)1.5
1.6

(4) Mixer. The plant shall include an approved continuous mixer adequately heated and capable of producing a uniform mixture within the job mix tolerances. It shall be equipped with a discharge hopper with dump gates to permit rapid and complete discharge of the mixture. The paddles shall be adjustable for an angular position mix. The mixer shall have a manufacturer's plate giving the net volumetric contents of the mixer at the several heights inscribed on a permanent gage and the rate of feed of aggregate per minute at plant operating speed. Unless otherwise required, the minimum mixing time shall be determined by dividing the weight of its contents at operating level by the weight of the mixture delivered per second by the mixer.

605
606
607
608
610
611
612
613
613
615
615
616
616

The weights for the job will be determined by tests made by the Engineer. The pugmill shall be equipped with a discharge hopper having a capacity of approximately 1 ton (90 kg). The hopper will be equipped with dump gates that will permit rapid and complete discharge of the bituminous mixture without segregation.

618
619
621
621
622

4.3 HAULING EQUIPMENT. Trucks used for hauling the bituminous mixture shall have tight, clean, smooth beds. To prevent the mixture from adhering to them, the truck beds shall be lightly coated with a minimum amount of concentrated hydrated lime and water solution. The truck beds shall be raised to drain any excess solution before loading the mixture in the trucks. Each truck shall have a suitable cover to protect the mixture from adverse weather or long hauls. An insulated bed may be required to maintain the mixture at the specified temperature during hauling.

625
628
628
629
630
631
631
632
632

4.4 BITUMINOUS PAVERS. Bituminous pavers shall be self-contained, power-propelled units with an activated screed or strike-off assembly, heated if necessary, and shall be capable of spreading and finishing courses of bituminous plant mix material which will meet the specified thickness, smoothness, and grade.

635
636
637
638
641

The paver shall have a receiving hopper of sufficient capacity to permit a uniform spreading operation. The hopper shall be equipped with a distribution system to place the mixture uniformly in front of the screed. The screed or strike-off assembly shall produce a finished surface of the required evenness and texture without tearing, shoving, or gouging the mixture.

643
645
645
646
646
649
649

The paver shall be capable of operating at forward speeds consistent with satisfactory laying of the mixture.

651
652

If an automatic grade control device is used, the paver shall be equipped with a control system capable of automatically maintaining the screed elevation as specified herein. The

655
655
657

ITEM P-402 POROUS FRICTION COURSE (Central Plant Hot Mix)	1.5 1.6
control system shall be automatically actuated from either a reference line or a surface through a system of mechanical sensors or sensor-directed mechanisms or devices which will maintain the paver screed at a predetermined transverse slope and at the proper elevation to obtain the required surface.	657 658 658 659 659
<u>4.5 ROLLERS.</u> A minimum of two self-propelled, steel-wheel rollers shall be furnished. They shall be in good condition, capable of reversing without backlash, and capable of operating at slow speeds to avoid displacement of the bituminous mixture. The wheels shall be equipped with adjustable scrapers, water tanks, and sprinkling apparatuses to prevent the bituminous mixture from sticking to the wheels. The weight of each roller shall be 6 to 12 tons (5 400 to 10 800 kg). The use of equipment which results in excessive crushing of the aggregate will not be permitted.	662 663 665 665 667 668 670 671 671
<u>4.6 PREPARATION OF MINERAL AGGREGATE.</u> The aggregate for the mixture shall be dried and heated at the central mixing plant before entering the mixer. When introduced into the mixer, the combined aggregate moisture content (weighted according to the composition of the blend) shall be less than 0.25 percent for aggregate blends with water absorption of 2.5 percent or less and less than 0.50 percent for aggregate blends with water absorption greater than 2.5 percent. Water absorption of aggregates shall be determined by ASTM C127 and ASTM C128. The water absorption for the aggregate blend shall be the weighted average of the absorption values for the coarse aggregate retained on the No. 4 sieve (4.75 mm) and the fine aggregate passing the No. 4 sieve (4.75 mm). The water content test will be conducted in accordance with ASTM C566. In no case shall the moisture content be such that foaming of the mixture occurs prior to placement. At the time of mixing, the temperature of the aggregate shall be within the range specified in the job mix formula. The maximum temperature and rate of heating shall be such that no damage occurs to the aggregates. Particular care shall be taken so that aggregates high in calcium or magnesium content are not damaged by overheating. The aggregate shall be screened to specified sizes and conveyed in separate bins ready for mixing with bituminous material.	674 675 677 678 678 679 680 681 682 682 683 684 685 686 687 689 690 690 692 693 694 695 695
<u>4.7 PREPARATION OF BITUMINOUS MIXTURE.</u> The bituminous mixture shall be prepared in a central mixing plant. The mixture shall be prepared at the temperature designated by the Engineer within the range shown in Paragraph 402-2.3.	698 699 699 699
The dry aggregate shall be combined in the plant in the proportionate amounts of each aggregate size required to meet the specified gradation. The quantity of aggregate for each batch shall be determined, measured, and conveyed into the mixer. In	701 702 703 706

ITEM P-402	POROUS FRICTION COURSE	1.5
	(Central Plant Hot Mix)	1.6

case of volumetric proportioning, <u>the size of the openings shall</u>	707
<u>be determined, and the gates shall be locked in position.</u>	708

<u>The quantity of bituminous material for each batch or the</u>	710
<u>calibrated amount for continuous mixers shall be determined by</u>	711
<u>the Engineer. It shall be measured by weight and introduced into</u>	712
<u>the mixer within the temperature range specified in the job mix</u>	712
<u>formula. For batch mixers, all aggregates shall be in the mixer</u>	714
<u>before the bituminous material is added. In no case shall the</u>	715
<u>temperature of the aggregate be more than 25 degrees F (4 degrees</u>	715
<u>C) above the temperature of the bituminous material when adding</u>	716
<u>the bituminous material. As determined by the Engineer, the</u>	717
<u>mixing shall continue until all particles are coated uniformly.</u>	718
<u>In no case shall the bituminous mixture be stored in storage</u>	719
<u>silos or surge bins.</u>	719

<u>4.8 TRANSPORTATION AND DELIVERY OF THE MIXTURE. The mixture</u>	722
<u>shall be transported from the central mixing plant to the paving</u>	722
<u>job in trucks described in Paragraph 402-4.3. The mixture shall</u>	724
<u>be placed at a temperature between 200 degrees F (94 degrees C)</u>	724
<u>and 295 degrees F (146 degrees C). Delivery of the mixture shall</u>	725
<u>be scheduled so that spreading and rolling of a day's production</u>	726
<u>can be completed during daylight hours the same day.</u>	726

<u>4.9 SPREADING AND LAYING.</u>	728
----------------------------------	-----

<u>(a) Preparation of Existing Surfaces. All porous friction</u>	731
<u>courses shall be constructed on an existing pavement surface that</u>	731
<u>is structurally sound; is in good condition; is constructed to</u>	734
<u>new pavement surface course smoothness criteria; and has Marshall</u>	735
<u>stability and flow values comparable to those specified in Item</u>	736
<u>P-401. The work involved in rehabilitating the existing pavement</u>	737
<u>surface shall be otherwise provided for in the contract and is</u>	738
<u>not a part of this PFC specification. Rehabilitation of the</u>	739
<u>existing pavement including: construction of bituminous overlay;</u>	740
<u>joint sealing; crack repair; reconstruction of failed pavement</u>	743
<u>areas; removal of rubber deposits; removal of pavement markings;</u>	745
<u>and cleaning of grease, oil, and fuel spills shall be completed</u>	748
<u>and accepted by the Engineer prior to the placement of the porous</u>	749
<u>friction course.</u>	749

<u>Immediately before placing the porous friction course, the</u>	752
<u>underlying course shall be cleared of all loose or deleterious</u>	752
<u>material with power blowers, power brooms, or hand brooms as</u>	754
<u>directed. A tack coat conforming to Item P-603 shall be placed,</u>	755
<u>as directed by the Engineer, on those existing surfaces where a</u>	757
<u>tack coat is necessary for bonding the PFC to the existing</u>	757
<u>surface. If emulsified asphalt is used, placement of the PFC can</u>	759
<u>be applied immediately. However, if cutback asphalt is used,</u>	761
<u>placement of the PFC must be delayed until the tack coat has</u>	762
<u>properly aired.</u>	762

ITEM P-402 POROUS FRICTION COURSE
(Central Plant Hot Mix)

1.5

1.6

(b) Placing. Hauling over material already placed shall not be permitted until the material has been thoroughly compacted as specified and allowed to develop its stability for a period of, at least, 12 hours. In areas where extremely hot temperatures occur, it is suggested that no traffic be allowed on the PFC until it has cooled overnight. Traffic should be discontinued if any closing of the PFC is observed. The bituminous mixture shall be placed at the required minimum lane width with an approved bituminous paver as specified in Paragraph 402-4.4.

765
766
767
768
769
770
771
771
772
772

thoroughly compacted with hot hand tampers.

807

Any mixture which becomes loose and broken, mixed with dirt, or in any way defective shall be removed and replaced with fresh hot

811

811

ITEM P-501 PORTLAND CEMENT CONCRETE PAVEMENT

1.5

1.6

When mixed at the work site or in a central mixing plant, the mixing time shall not be less than 50 seconds nor more than 90 seconds. Mixing time ends when the discharge chute opens. Transfer time in multiple drum mixers is included in mixing time. The contents of an individual mixer drum shall be removed before a succeeding batch is emptied therein.

946

946

947

948

949

950

The mixer shall be operated at the drum speed as shown on the manufacturer's nameplate on the approved mixer. Any concrete mixed less than the specified time shall be discarded at the Contractor's expense. The volume of concrete mixed per batch shall not exceed the mixer's nominal capacity in cubic feet (cubic meters), as shown on the manufacturer's standard rating plate on the mixer. An overload up to 10 percent above the mixer's nominal capacity may be permitted provided concrete test data for segregation and uniform consistency are satisfactory, and provided no spillage of concrete takes place. The batch shall be charged into the drum so that a portion of the mixing water shall enter in advance of the cement and aggregates. The flow of water shall be uniform, and all water shall be in the drum by the end of the first 15 seconds of the mixing period. The throat of the drum shall be kept free of such accumulations as may restrict the free flow of materials into the drum.

952

954

955

956

957

958

959

960

961

963

964

965

966

967

968

969

Mixed concrete from the central mixing plant shall be transported in truck mixers, truck agitators, or nonagitating trucks. The time elapsing from the time water is added to the mix until the concrete is deposited in place at the work site shall not exceed 30 minutes when the concrete is hauled in nonagitating trucks, nor 60 minutes when the concrete is hauled in truck mixers or truck agitators. Retempering concrete by adding water or by other means will not be permitted, except when concrete is delivered in transit mixers. With transit mixers additional water may be added to the batch materials and additional mixing performed to increase the slump to meet the specified requirements, if permitted by the Engineer. All these operations must be performed within 45 minutes after the initial mixing operations and the water-cement ratio must not be exceeded. Admixtures for increasing the workability or for accelerating the set will be permitted only when specified for in the contract.

971

975

975

976

977

978

979

980

981

982

983

985

986

987

988

3.9 LIMITATIONS OF MIXING. No concrete shall be mixed, placed, or finished when the natural light is insufficient, unless an adequate and approved artificial lighting system is operated.

992

994

994

Unless authorized in writing by the Engineer, mixing and concreting operations shall be discontinued when a descending air temperature in the shade and away from artificial heat reaches 40 degrees F (4 degrees C) and shall not be resumed until an ascending air temperature in the shade and away from artificial heat reaches 35 degrees F (2 degrees C).

997

998

998

999

1000

1000

ITEM P-501 PORTLAND CEMENT CONCRETE PAVEMENT

1.5

1.6

When concreting is authorized during cold weather, the aggregates may be heated by either steam or dry heat prior to being placed in the mixer. The apparatus used shall heat the mass uniformly and shall be arranged to preclude the possible occurrence of overheated areas which might be detrimental to the materials. Unless otherwise authorized, the temperature of the mixed concrete shall not be less than 50 degrees F (10 degrees C) at the time of placement in the forms.

1003

1004

1005

1006

1007

1009

1009

1010

If the air temperature is 35 degrees F (2 degrees C) or less at the time of placing concrete, the Engineer may require the water and/or the aggregates to be heated to not less than 70 degrees F (21 degrees C) nor more than 150 degrees F (66 degrees C). Concrete shall not be placed on frozen subgrade nor shall frozen aggregates be used in the concrete.

1012

1013

1014

1014

1015

1016

During periods of warm weather when the maximum daily air temperature exceeds 85 degrees F (30 degrees C), the following precautions should be taken. The forms and/or the underlying material shall be sprinkled with water immediately before placing the concrete. The concrete shall be placed at the coolest temperature practicable, and in no case shall the temperature of the concrete when placed exceed 90 degrees F (32 degrees C). The aggregates and/or mixing water shall be cooled as necessary to maintain the concrete temperature at or not more than the specified maximum.

1018

1020

1021

1022

1023

1024

1026

1026

1027

1027

3.10 PLACING CONCRETE.

1029

(a) Side-form Method. For the side-form method, the concrete shall be deposited on the moistened grade to require as little rehandling as possible. Unless truck mixers, truck agitators, or nonagitating hauling equipment are equipped with means for discharge of concrete without segregation of the materials, the concrete shall be unloaded into an approved spreading device and mechanically spread on the grade to prevent segregation of the materials. Placing shall be continuous between transverse joints without the use of intermediate bulkheads. Necessary hand spreading shall be done with shovels -- not rakes. Workmen shall not be allowed to walk in the freshly mixed concrete with boots or shoes coated with earth or foreign substances.

1033

1034

1036

1037

1038

1039

1040

1041

1042

1043

1043

1044

1045

1045

When concrete is to be placed adjoining a previously constructed lane of pavement and when mechanical equipment will be operated upon the existing lane of pavement, the concrete shall be at least 7 days old and at a flexural strength approved by the Engineer. If only finishing equipment is carried on the existing lane, paving in adjoining lanes may be permitted after 3 days, if approved by the Engineer.

1047

1048

1050

1051

1052

1054

ITEM P-620 RUNWAY AND TAXIWAY PAINTING

1.5

1.6

\$*

123

124.1

The Engineer shall specify the time period. TT-P-001952 may be applied 24 hours after placement of the pavement. In order to allow adequate curing of the pavement surface and to prevent peeling and blistering of the paint, a 30-day period is recommended for TT-P-85. Lesser periods may be specified if necessary to open the pavement to traffic. In this instance the Engineer may wish to specify temporary markings at 50 percent of the specified coverage and to repaint the markings after the asphalt has cured.

126

127

127

129

130

132

132

133

134

135.2

\$*

136

The edges of the markings shall not vary from a straight line more than 1/2 inch (12 mm) in 50 feet (15 m), and the dimensions shall be within a tolerance of plus or minus 5 percent. [Glass spheres shall be distributed to the surface of the marked areas immediately after application of the paint. A dispenser shall be furnished which is properly designed for attachment to the marking machine and suitable for dispensing glass spheres. The spheres shall be applied at the rate of 10 pounds per gallon of paint.]

140

142

143

143

145

146

147

147

147

The Contractor shall furnish certified test reports for the materials shipped to the project. The reports shall not be interpreted as a basis for final acceptance. The Contractor shall notify the Engineer upon arrival of a shipment of paint to the job site. All emptied containers shall be returned to the paint storage area for checking by the Engineer. The containers shall not be removed from the airport or destroyed until authorized by the Engineer.

149

151

152

153

154

156

156

157

3.6 PROTECTION. After application of the paint, all markings shall be protected from damage until the paint is dry. All surfaces shall be protected from disfiguration by spatter, splashes, spillage, or drippings of paint.

161

162

162

165

4. METHOD OF MEASUREMENT

167

4.1 The quantity of runway and taxiway markings to be paid for shall be [the number of square feet (square meters) of paint] [one complete item in place] performed in accordance with the specifications and accepted by the Engineer.

169

170

172

173

ITEM P-620 RUNWAY AND TAXIWAY PAINTING

1.5
1.65. BASIS OF PAYMENT

175

5.1 Payment shall be made at the [contract unit price per square foot (square meter)] [contract lump sum] for runway and taxiway painting. This price shall be full compensation for furnishing all materials and for all labor, equipment, tools, and incidentals necessary to complete the item.

178
180
181
185
185

Payment will be made under:

187

Item P-620-5.1 Runway and Taxiway Painting - [Per Square Foot (Square Meter)] [Lump Sum]

191
1926. MATERIAL REQUIREMENTS

194

Federal Specification Paint, Traffic: Reflectorized for Airfield
TT-P-85 Runway Marking (Drop-On-Type) 199
202
204

Federal Specification Paint, Traffic and Airfield Marking, Acrylic
TT-P-001952 Emulsion, For Use Reflectorized or 209
213
Non-Reflectorized 216

Federal Specification Paint, Traffic Black, (Nonreflectorized)
TT-P-110 221
223
225

Federal Specification Beads, (Glass Spheres); Retro-Reflective
TT-B-1325 230
232
234

++ END OF ITEM P-620 ++

235.3

ITEM P-402 POROUS FRICTION COURSE
(Central Plant Hot Mix)1.5
1.6

(1) Weigh box or hopper. The equipment shall include a means for accurately weighing each size of aggregate in a weigh box or hopper of ample size to hold a full batch without hand raking or running over. The gate shall close tightly so that no material is allowed to leak into the mixer while a batch is being weighed.

507
508
509
511
512
512

(2) Bituminous control. The equipment used to measure the bituminous material shall be accurate to within plus or minus 0.5 percent. The bituminous material bucket shall be of a nontilting type with a loose sheet metal cover. The length of the discharge opening of the spray-bar shall be not less than three-fourths the length of the mixer, and it shall discharge directly into the mixer. The bituminous material bucket, its discharge valve(s), and the spray-bar shall be adequately heated. Steam jackets, if used, shall be efficiently drained, and all connections shall be constructed so that they will not interfere with the efficient operation of the bituminous scales. The capacity of the bituminous material bucket shall be at least 15 percent of the weight of bituminous material required in any batch. The plant shall have an adequately heated, quick-acting, nondrip charging valve located directly over the bituminous material bucket.

515
516
517
518
518
520
522
523
527
527
527
527
529
529
530
532
532
532

The indicator dial shall have a capacity of at least 15 percent in excess of the quantity of bituminous material used per batch. The controls shall be constructed to lock at any dial setting and automatically reset to that reading after each additional batch of bituminous material. The dial shall be in full view of the mixer operator. The flow of bituminous material shall be automatically controlled to begin when the dry mixing period is over. All of the bituminous material required for one batch shall be discharged in not more than 15 seconds after the flow has begun. The size and spacing of the spray-bar openings shall provide a uniform application of bituminous material the full length of the mixer. The section of the bituminous line between the charging valve and the spray-bar shall have a valve and an outlet for checking the meter when a metering device is substituted for a bituminous material bucket.

534
535
536
537
538
539
540
541
542
543
544
545
545
546
547

(3) Mixer. The batch mixer shall be an approved type capable of producing a uniform mixture with well-coated aggregate in the prescribed mixing time within the job mix tolerance specified. If not enclosed, the mixer box shall be equipped with a hood to prevent loss of dust.

550
551
552
554
554

(4) Control of mixing time. The mixer shall be equipped with an accurate time lock to control the operations of a complete mixing cycle. It shall lock the weigh-box gate after the charging of the mixer and keep it locked until the closing of the mixer gate at the completion of the cycle. It shall lock the

557
557
559
560
561

ITEM P-402 POROUS FRICTION COURSE
(Central Plant Hot Mix)1.5
1.6

bucket throughout the dry mixing period and shall lock the mixer gate throughout the dry and wet mixing periods. The dry mixing period is the time interval between the opening of the weigh-box gate and the introduction of bituminous material. The wet mixing period is the time interval between the introduction of the bituminous material and the opening of the mixer gate.

561
562
562
563
564
564

The timing control shall be flexible and shall be capable of settings at 5-second intervals or less throughout a 3-minute cycle. A mechanical batch counter shall be installed as a part of the timing device and shall be designed to register only completely mixed batches.

566
567
568
569
569

The setting of time intervals shall be at the direction of the Engineer who shall then lock the case covering the timing device. It shall remain locked until a change is made in the timing periods.

571
572
573
573

(c) Requirements for Continuous Plants.

575

(1) Aggregate proportioning. The plant shall include means for accurately proportioning each size of aggregate.

578
578

The plant shall have a feeder mounted under each compartment bin. Each compartment bin shall have an accurately controlled individual gate to form an orifice for the volumetric measuring of material drawn from each compartment. The feeding orifice shall be rectangular with one dimension adjustable by positive mechanical means and provided with a lock.

580
581
582
584
585
585

Indicators shall be provided for each gate to show the respective gate opening in inches.

587
587

(2) Weight calibration of aggregate feed. The plant shall include a means to calibrate gate openings by weighing test samples. Provision shall also be made so that materials fed out of individual orifices may be bypassed to individual test boxes. The plant shall be equipped to conveniently handle individual test samples of not less than 200 pounds (92 kg). Accurate scales shall be provided by the Contractor to weigh such samples. Charts showing the rate of feed per minute for each hot bin shall be provided.

590
591
593
593
594
596
596
597
597

(3) Synchronization of aggregate feed and bituminous materials feed. A satisfactory interlocking mechanical means or any other positive method approved by the Engineer shall be provided to afford positive interlocking control between the flow of aggregate from the bins and the flow of bituminous material from the meter or other proportioning device.

599
600
600
601
602
602

ITEM P-402 POROUS FRICTION COURSE (Central Plant Hot Mix)	1.5 1.6
mixture and immediately compacted to conform to the surrounding area. This work will be done at the Contractor's expense. Skin patching and handworking of the PFC mixture will not be allowed.	812 814 814
4.11 JOINTS. The formation of all joints shall be made in such a manner as to ensure a continuous bond between old and new sections of the course. All joints shall present the same texture, density, and smoothness as other sections of the course.	817 818 819 819
The roller shall not pass over the unprotected end of the freshly laid mixture except when necessary to form a transverse joint. When necessary to form a transverse joint, it shall be made by means of placing a bulkhead or by tapering the course, in which case the edge shall be cut back to its full depth and width on a straight line to expose vertical face. In both methods all contact surfaces shall be given a tack coat of bituminous material before placing any fresh mixture against the joint.	821 822 824 825 826 827 828 828
Longitudinal joints which are irregular, damaged, or otherwise defective shall be cut back to expose a clean, sound surface for the full depth of the course. All contact surfaces shall be given a tack coat of bituminous material prior to placing any fresh mixture against the joint. The longitudinal joint shall offset that in the existing course by at least 1 foot (30 cm).	831 832 833 834 835 835
4.12 SHAPING EDGES. While the surface is being compacted and finished, the Contractor shall carefully shape the longitudinal outside edges of the PFC to a vertical face at the established edge. When transitioning from PFC to existing pavement, transverse edges shall be constructed with a finer graded bituminous mixture.	838 839 840 841 842 842
4.13 SURFACE TESTS. After completion of the final rolling, the finished surface shall be tested with a 16-foot (5 m) straightedge and shall not vary more than 1/4 inch (6 mm). The 16-foot (5 m) straightedge shall be applied parallel with and at right angles to the runway centerline in a pattern that includes longitudinal and transverse joints. The 16-foot (5 m) straightedge shall be advanced approximately 1/2 its length in the line of measurement.	846 846 848 848 849 850 851 851
Areas of the porous friction course exceeding the specified tolerances shall be corrected at the Contractor's expense by removing the defective work and replacing it with new material. Skin patching or handworking will not be permitted.	853 854 855 856
4.14 SAMPLING PFC MIXTURE AND HOT BINS. Samples of the PFC mixture shall be taken at the point of discharge in hauling units and tested to control uniformity in the bituminous content and gradation. Samples shall be taken in accordance with ASTM D979. Enough mixture shall be taken to prepare duplicate tests on each	859 861 862 863 864

ITEM P-402 POROUS FRICTION COURSE
(Central Plant Hot Mix)1.5
1.6

sample of mixture in accordance with ASTM D2172. Samples shall be taken, at least, once for any central plant-run of more than 30 minutes and at least twice for any central plant-run of more than 5 hours. 866
868
869
869

Should the bituminous content of the duplicate tests agree within 0.50 percent, the average results shall be recorded. Variations greater than 0.50 percent between duplicate tests of the same sample shall also be recorded, and duplicate tests on an additional sample shall be run. The average value of the bituminous content should fall within the tolerance of the job mix formula as specified in Paragraph 402-3.2. Should the average bituminous content for four samples not fall within the job mix tolerances, the Engineer may order the Contractor to cease production until such out-of-tolerance conditions have been remedied by the Contractor. The gradation of the residual aggregate should be determined by using AASHTO T30 and compared to the approved job mix formula. 871
873
873
874
875
875
877
878
879
881
881
882

The samples of PFC mixture will be used to control the uniformity of the Contractor's plant production. In addition, the Contractor shall clearly mark each hauling unit from which the representative samples have been taken so that the same mixture sample may be located in the completed pavement. 884
887
888
889
889

Completed PFC shall be determined "acceptable" or "unacceptable" on the basis of visual inspection by the Engineer. The Engineer shall immediately notify the Contractor of visual defects such as nonuniform texture, roller marks, bleeding of bituminous material, cracking and shoving of the mixture, and evidence of aggregate crushing during the roller operations, or nonconformance to the surface smoothness criteria as specified in Paragraph 402-4.13. 891
893
894
896
898
899
900
900

"Unacceptable" PFC shall be removed, leaving a vertical face at the remaining PFC. The underlying surface shall be cleaned and a tack coat applied prior to replacing the PFC. All work shall be at the Contractor's expense. Unacceptable PFC shall not be measured for payment. 903
904
906
907
907

In addition to sampling and testing the PFC mixture, the Engineer shall sample each hot bin twice daily and furnish a gradation analysis of each hot bin according to ASTM C136. The combined gradation analysis of the hot bins shall fall within the job mix formula tolerances. Should the hot bin gradation analysis fail to meet the tolerances of the job mix formula (on the same sieve size), the Engineer may order another analysis in addition to the two analyses required each day to confirm the results of the previous tests or tell the Contractor to cease plant production until such out-of-tolerance conditions have been corrected. 910
911
912
912
914
915
916
917
918
919

ITEM P-402 POROUS FRICTION COURSE (Central Plant Hot Mix)	1.5 1.6
4.15 BITUMINOUS AND AGGREGATE MATERIAL (CONTRACTOR'S RESPONSIBILITY). Samples of the bituminous and aggregate materials that the Contractor proposes to use, together with a statement of their source and character, shall be submitted for approval prior to use. The Contractor shall require the manufacturer or producer of the bituminous and aggregate materials to furnish material subject to this and all other pertinent requirements of the contract. Only those materials which have been tested and approved for the intended use shall be acceptable.	921 922 924 926 927 928 928 928 930 930 930 930
The Engineer or the Engineer's authorized representative shall have access, at all times, to all parts of the paving plant to inspect the equipment, the conditions, and the operation of the plant; to verify the weights or proportions and character of materials; and to determine the temperatures maintained in the storage of the bituminous material and preparation of the mixtures.	933 935 937 938 939 940 940
The Contractor shall furnish the vendor's certified test reports for each carload or equivalent of bituminous material shipped to the project. The report shall be delivered to the Engineer before permission is granted to use the material. The vendor's certified test report for the bituminous material shall not be interpreted as a basis for final acceptance. All test reports shall be subject to verification by testing sample materials received for use on the project.	942 943 944 945 945 947 947 948
4.16 PROTECTION OF PAVEMENT. After final rolling, no vehicular traffic of any kind shall be permitted on the pavement until it has cured at least 12 hours. Newly constructed pavement areas shall not be opened to aircraft traffic until 24 hours after completion or unless otherwise authorized by the Engineer.	952 952 954 955 955
5. METHOD OF MEASUREMENT	957
5.1 Porous friction course shall be measured by the number of [square yards (square meters)] [tons (kg)] of mixture used in the accepted work.	959 961 961
Only the areas of the porous friction course meeting the following thickness requirements shall be measured for payment:	963 964
To determine the thickness of the finished PFC, the Engineer shall take one core sample, not less than 2 inches (5 cm) in diameter, at random from each unit of the completed PFC area. A unit of the completed area shall be one paving lane wide by 1,000 feet (304 m) long. The last unit in any one paving lane shall include any remaining length in addition to the 1,000 feet (304 m).	967 968 969 971 972 972 972

ITEM P-402 POROUS FRICTION COURSE
(Central Plant Hot Mix)1.5
1.6

When the measurement of any core is more than the maximum or less than the minimum allowable thickness, as shown in Table 3, additional cores shall be taken at 20-foot intervals (.6 m) (parallel to and at right angles to the runway centerline) until the completed PFC is within such maximum or minimum thickness for the subunit being tested. Out-of-tolerance areas shall be deducted from the total [square yards (square meters)] [tons (kg)] PFC for payment. If, in the Engineer's judgment, such out-of-tolerance areas warrant removal, the PFC shall be removed and the underlying course shall be cleaned (ready for reconstruction), all at the Contractor's expense.

974
975
976
976
977
979
980
982
983
984
985
985TABLE 3. ALLOWABLE FINISHED PFC THICKNESS

988

	Nominal in. mm	Maximum in. mm	Minimum in. mm
3/4 in. Aggregate	1.0 25	1.50 37	0.75 19
1/2 in. Aggregate	0.75 19	1.25 32	0.50 12

990
991
992
993
9946. BASIS OF PAYMENT

997

6.1 Payment shall be made at the respective contract prices per [square yard (square meter)] [ton (kg)] for porous friction course and per [gallon (liter)] [ton (kg)] for bituminous material. The prices shall be full compensation for furnishing all materials; for all preparation and storage of materials; for cleaning the existing surface; for mixing, hauling, placing, and compacting the mixture (including initial test section); and for all tools, equipment, and incidentals necessary to complete each item. No separate payment is included in the contract for furnishing and batching mineral filler, or antistripping agents, should such items be required.

1000
1003
1006
1008
1010
1014
1016
1018
1019
1021
1022

Rehabilitation of the existing pavement surface and the tack coat shall be measured and paid for at their respective contract prices.

1025
1025
1025

Payment will be made under:

1027

Item P-402-6.1 Porous Friction Course - [Per square yard (square meter)] [ton (kg)]

1031
1032

Item P-402-6.1 Bituminous Material - [Per gallon (liter)] [ton (kg)]

1036
1037

ITEM P-402	POROUS FRICTION COURSE	1.5
	(Central Plant Hot Mix)	1.6

7. TESTING REQUIREMENTS

<u>ASTM C29</u>	<u>Unit Weight of Aggregate</u>	1042
<u>ASTM C88</u>	<u>Soundness of Aggregates by Use of Sodium Sulfate or Magnesium Sulfate</u>	1045 1046
<u>ASTM C127</u>	<u>Specific Gravity and Absorption of Coarse Aggregate</u>	1049 1050
<u>ASTM C128</u>	<u>Specific Gravity and Absorption of Fine Aggregate</u>	1053 1054
<u>ASTM C131</u>	<u>Resistance to Abrasion of Small Size Coarse Aggregate by Use of the Los Angeles Machine</u>	1057 1058
<u>ASTM C136</u>	<u>Sieve or Screen Analysis of Fine and Coarse Aggregates</u>	1061 1062
<u>ASTM C566</u>	<u>Total Moisture Content of Aggregate by Drying</u>	1065
<u>ASTM D693</u>	<u>Crushed Stone, Crushed Slag, and Crushed Gravel for Bituminous Macadam Base and Surface Courses of Pavements</u>	1068 1069 1070
<u>ASTM D979</u>	<u>Sampling Bituminous Paving Mixtures</u>	1073
<u>ASTM D1664</u>	<u>Coating and Stripping of Bitumen - Aggregate Mixtures</u>	1076 1077
<u>ASTM D2172</u>	<u>Quantitative Extraction of Bitumen from Bituminous Paving Mixtures</u>	1080 1081
<u>AASHTO T30</u>	<u>Mechanical Analysis of Extracted Aggregate</u>	1084

8. MATERIAL REQUIREMENTS

<u>ASTM D242</u>	<u>Mineral Filler for Bituminous Paving Mixtures</u>	1089
<u>ASTM D946</u>	<u>Asphalt Cement for Use in Pavement Construction</u>	1092 1093
<u>ASTM D3381</u>	<u>Viscosity-Graded Asphalt Cement for Use in Pavement Construction</u>	1096 1097
<u>AASHTO M226</u>	<u>Viscosity Graded Asphalt Content</u>	1100
+ + END OF ITEM P-402 + +		1101.3